

▶ DPF 6500 Vinyl Film

Premium Translucent Cast Digital Film

DPF 6500 is a 50 microns gloss white, cast, translucent film with permanent pressure-sensitive adhesive. Designed for backlit graphics, DPF 6500 is made of premium cast face stock with a special lay-flat liner. The film provides superior print resolution and image quality. DPF 6500 is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Digital printing with a wide variety of direct print systems
- Internally illuminated signage, displays and where light transmission is important
- Use in conjunction with Series 3200, Series 3210, Series 3220 or Series 3350 overlaminates

Certified for
HP Latex Inks

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	25 to 40 Gloss Units
THICKNESS	Micrometer, Federal Bench Type	50 microns
TENSILE STRENGTH	Tensile Tester 51mm jaw separation; crosshead speed of 5.1 mm/s, web direction	≥ 0.8 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 150%
SHELF LIFE (IN BOX)	Ideal storage temperature 21°C and 50% relative humidity	1 year from factory shipment
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	4.4°C to 38°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°C to 93°C
DIMENSIONAL STABILITY	70°C, 48 hours aging	0.25 mm
PEEL ADHESION	PSTC-1, 15 min, 21°C	0.45 kg/cm
LINER RELEASE	TLMI Release at 90°, 760 cm/min	0.03 kg/2 cm

Standard Terms & Conditions Apply
NOTE: DPF 6500 has a 27% light transmission.

OPTIMUM PERFORMANCE

DPF 6500 is a premium cast translucent vinyl film that has been weather tested in a variety of rigorous direct exposure locales, including Florida and California.

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility. DPF 6500 will resist weathering best when applied to vertical or upper outboard angles. Arlon does not recommend its film for horizontal and close horizontal applications.

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

April 2020

USA

 200 Boysenberry Lane, Placentia, CA 92870

 800 232 7161 / +1 714 985 6300

 +1 714 985 6305

EUROPE

 Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands

 +31 70 354 4311

 +31 70 355 7721

CHINA

 No. 1989 Xinchang Road, Weifang, Shandong, 262400

 +86 0536 6226568