



## ► DPF V9500

### Premium Non-PVC Digital Wall Wrap Film

DPF V9500 is a premium, 2-mil (50 micron) printable non-PVC polyurethane film designed for use on textured wall surfaces. With its excellent conformability and heat reception, DPF V9500 enables a fast and efficient installation on highly textured and irregular surfaces to deliver a paint-like finish. The permanent tinted adhesive and air-egress liner is engineered for optimal initial tack and repositionability during installation while enabling a long-lasting ultimate bond to the substrates over the life of the installation. The film also has excellent dimensional stability suitable for hot and cold installation. The polyurethane film offers an extended durability of up to 10 years (unprinted) and is compatible with Eco-Solvent, Solvent, Latex, and UV print systems.

### APPLICATIONS & FEATURES

- Recommended for indoor and outdoor graphics and signs. Smooth and textured surfaces.
- 68% reduction in VOCs during manufacturing as compared with PVC cast film
- Excellent conformability to highly textured and irregular surfaces for paint-like finish install
- Optimal initial tack and long-term permanent adhesive engineered specifically for wall application
- Wide installation temperature ranges from 40F to 90F
- Fire Certified to ASTM E84, EN 13501 and AS 5637
- Compatible with Series V3370 Satin

Certified for  
HP Latex Inks

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	> 70 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	2-mil (50 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	> 13 lbf/in	> 22.76 n/cm
ELONGATION	Instron Tensile Tester as above	≥ 300%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	2 Year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	50°F to 95°F	10°C to 35°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-40°F to 200°F	-20°C to 93.3°C
DIMENSIONAL STABILITY	Shrinkage after 158°F (70°C), 48 hours aging	0.005 in	0.127 mm
PEEL ADHESION	PSTC-1, 15 min, RT 70°F (21°C)	3.4 lbf/in	5.95 n/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	70 g/2 in	13.78 g/cm

*Expected performance life for textured surface graphics of 6-24 months outdoor when not used in freezing and thawing cycles.  
Subject to the type of surface and its environmental conditions*

#### USA

- a 200 Boysenberry Lane, Placentia, CA 92870
- p 800 232 7161 / +1 714 985 6300
- f +1 714 985 6305

#### EUROPE

- a Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
- p +31 70 354 4311
- f +31 70 355 7721

#### CHINA




- a No. 1989 Xinchang Road, Weifang, Shandong, 262400
- p +86 0536 6226568

## TERMS & CONDITIONS




The warranties offered in Arlon's Standard Terms and Conditions, which are incorporated in full by this reference and are available at [https://www.arlon.com/na\\_en/legal/terms-and-conditions](https://www.arlon.com/na_en/legal/terms-and-conditions), are made in lieu of all other express or implied warranties.

June 2025



### USA

-  200 Boysenberry Lane, Placentia, CA 92870
-  800 232 7161 / +1 714 985 6300
-  +1 714 985 6305

### EUROPE

-  Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
-  +31 70 354 4311
-  +31 70 355 7721

### CHINA

-  No. 1989 Xinchang Road, Weifang, Shandong, 262400
-  +86 0536 6226568