



► ProTec Series 3960

Heavy Duty Overlamine

ProTec Series 3960 overlamine is a 12-mil (305 micron) film with a clear, permanent pressure-sensitive adhesive. The heavy gauge product is designed to protect decals and graphics while maintaining high clarity. ProTec Series 3960 is rated for an outdoor durability up to 2 years.

APPLICATIONS & FEATURES

- Protective overlamine for racing, dirt bikes, and other recreational vehicles
- Ideal for applications needing exceptional durability and abrasion resistance
- Designed to be laminated cold without any heat
- Excellent clarity and gloss retention
- Minimize silvering and enhance image quality with fast wet-out adhesive system

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	70 to 90 Gloss Units	
THICKNESS	Micrometer, Federal Bench Type	12-mil (305 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 45.67 lb/in	≥ 8.16 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 270%	
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	50°F to 80°F	10°C to 26°C
SERVICE TEMPERATURE RANGE	Film applied to etched aluminum panels 24 hours prior to testing	-40°F to 176°F	-40°C to 80°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours, on aluminum panel	20-mil	0.51 mm
PEEL ADHESION	PSTC-1, 15 min. 70°F (21°C)	≥ 3.00 lbs/in	≥ 0.54 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	38 g/2 in	7.48 g/cm
HUMIDITY RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing. 100% relative humidity, 100°F (38°C) for 500 hours.	No Appreciable Effect	
GASOLINE RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing. Immersed 30 minutes at 70°F (21°C), stabilized for 24 hours before inspection.	No Appreciable Effect	

Standard Terms & Conditions Apply

USA

- a** 200 Boysenberry Lane
Placentia, CA 92870
- p** 800 232 7161 / +1 714 985 6300
- f** +1 714 985 6305

EUROPE

- a** Koninginnegracht 10 2514 AA
Den Haag, The Netherlands
- p** +31 70 354 4311
- f** +31 70 355 7721

AUSTRALIA

- a** 18 Axis Crescent
Dandenong South, VIC 3175
- p** +61 3 8751 7999

CHINA




- a** No. 1989 Xinchang Road
Weifang, Shandong, 262400
- p** +86 0536 6226568




TERMS & CONDITIONS

The warranties offered in Arlon’s Standard Terms and Conditions, which are incorporated in full by this reference and are available at https://www.arlon.com/na_en/legal/terms-and-conditions, are made in lieu of all other express or implied warranties.




October 2025

USA



-  200 Boysenberry Lane
Placentia, CA 92870
-  800 232 7161 / +1 714 985 6300
-  +1 714 985 6305

-  6110 Rittiman Road
San Antonio, TX 78218
-  800 549 9860 / +1 210 798 1900
-  +1 210 798 1939

EUROPE

-  Koninginnegracht 10 2514 AA
Den Haag, The Netherlands
-  +31 70 354 4311
-  +31 70 355 7721

AUSTRALIA

-  18 Axis Crescent
Dandenong South, VIC 3175
-  +61 3 8751 7999

CHINA

-  No. 1989 Xinchang Road
Weifang, Shandong, 262400
-  +86 0536 6226568