**PRODUCT INFORMATION BULLETIN** 



# Series 3460 Overlaminate

### Premium Calendered Overlaminate Gloss and Matte Finishes

Series 3460 is a 2.2-mil (55 micron) calendered vinyl film with clear, permanent pressure-sensitive adhesive. Designed to protect and prolong the life of printed images, Series 3460 has a full polymeric facestock and is available in gloss and matte finishes. The 55 micron facestock of Series 3460 provides a higher conformability for vehicle wraps, intermediate signages, and graphics. Series 3460 is rated for outdoor durability up to 7 years.

### **APPLICATIONS & FEATURES**

- Protective overlaminate for DPF 4650GLX
- Vehicle graphics, intermediate signage, kiosks and POP displays
- UV inhibitors to protect and extend the life of your printed graphic
- Series 3460 is not designed to be used as an optically clear window film.
- Arlon overlaminate film is designed to be laminated cold without any heat

## **PERFORMANCE & PHYSICAL DATA**

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	≥ 75 Gloss Units (Gloss) ≤ 20 Gloss Units (Matte)	
THICKNESS	Micrometer, Federal Bench Type	2.2-mil (55 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min, (5.1 mm/s), web direction	$\geq$ 7 lb/in width	≥ 1.24 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥ 170%	
SHELF LIFE (IN BOX)	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 80°F	15°C to 27°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
DIMENSIONAL STABILITY	Shrinkage After 158°F (70°C), 48 hours	≤ 24 mil	≤ 0.61 mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 2.0 lb/in	≥ 0.35 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	70 g/2in	14 g/cm

Note: Stiffness from calendared film may not conform as well to surface topography of UV inks. Standard Terms & Conditions Apply

USA

#### EUROPE

- a 200 Boysenberry Lane, Placentia, CA 92870
- 800 232 7161 / +1 714 985 6300
- f +1 714 985 6305

a) Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands
b) +31 70 354 4311

### CHINA

a No. 1989 Xinchang Road, Weifang, Shandong, 262400
+86 0536 6226568

**f** +31 70 355 7721

### **TERMS & CONDITIONS**

The following is made in lieu of all warranties expressed or implied:

All orders and purchases made in connection with this document are governed and limited by Arlon's Standard Terms and Conditions, which are incorporated in full by this reference and are available at http://www.arlon.com/terms-and-conditions or in hardcopy by request.

USA

#### EUROPE

- a 200 Boysenberry Lane, Placentia, CA 92870
- 800 232 7161 / +1 714 985 6300
- **f** +1 714 985 6305

### a Dr. Lelykade 22B, 2583CM Den Haag, The Netherlands

#### **p** +31 70 354 4311

**f** +31 70 355 7721

### CHINA

a No. 1989 Xinchang Road, Weifang, Shandong, 262400
+86 0536 6226568