



▶ DPF 210PB Polyester Roll-Up Banner

Digital Print Banner – Pebble Texture

DPF 210PB is a 9.8-mil (250 micron) premium, pebble textured, semi-rigid, coated polyester banner that is used in roll-up or pop-up banner applications. It has a gray, block-out layer that provides excellent opacity. DPF 210PB yields high print resolution and image quality, and has excellent lay-flat properties with minimal edge-curl. DPF 210PB is compatible with Eco-Solvent, Solvent and Latex* inks. DPF 210PB is rated for indoor durability up to 1 year. Please use proper handling and correct profiles with appropriate heater settings for optimal prints*.

APPLICATIONS & FEATURES

- Digital printing with a wide variety of direct print systems
- Indoor roll-up and pop-up display systems
- Exhibitions, advertisements and POP displays

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
WEIGHT	Internal Test Method	510 +/- 20 gram/sqm (15 +/- 0.25 oz/sqyd)
THICKNESS	Micrometer, Federal Bench Type	9.8-mil (250 micron)
COLOR	CIELAB	1.5 from Color Standard
OPACITY / CONTRAST RATIO	Internal Test Method	90% - 100%
GLOSS	Gloss Meter at 60° Reflection	< 15 Gloss Units
TENSILE STRENGTH (WARP, WEFT)	ASTM D-882	Min. 100 lbs/in, 125 lbs/in 17.9 kg/cm, 22.3 kg/cm
ELONGATION (WARP, WEFT)	ASTM D-882	Min. 150%, 75%
TEAR STRENGTH (WARP, WEFT)	ASTM D-1004	Min. 35 lbs/in, 35 lbs/in 6.25 kg/cm, 6.25 kg/cm
PRINTING	Internal Test Method	Eco-Solvent, Solvent, Latex*
SHELF LIFE (IN BOX)	Free from excessive moisture, temperature, direct sunlight	1 year from production date
STORAGE TEMPERATURE	Internal Test Method	85°F or lower

Standard Terms & Conditions Apply

*Compatible with HP 360 Latex printer




❖Optimal print quality achieved by using pre-heat settings between 38°C and 43°C, Platen/Print heat settings between 40°C and 45°C Post/dryer setting at 55°C or maximum, recommended profiles and proper handling.







TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

December 2016

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands
UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK

 800 232 7161/+1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721
 +44 161 884 0592  +31 70 355 7721

arlon.com